

Product Description

TREMstop® IA+ is a high-performance, single-component, water-based, firestop sealant that will expand to fill the voids left when combustible materials burn and deteriorate in a fire.

Basic Uses

TREMstop IA+ is tested to treat the majority of the common applications found on a job site, including metal pipe, plastic pipe, insulated pipe, cables, ducts and multiple penetrations.

Features and Benefits

- Advanced performance capabilities make TREMstop IA+ a best in class intumescent acrylic. This versatile firestopping product has exceptional sealant qualities, including superb unprimed adhesion, easy gunning and antifungal properties. It can also be painted once fully cured.
- TREMstop IA+ will also seal against airflow, which will help to reduce sound transmission for openings breached by penetration.

Availability

Immediately available from your local Tremco Field Representative, Tremco Distributor or Tremco Warehouse.

Coverage Rates

308' of joint per gal for a 1/4" x 1/4" (6 mm x 6 mm) joint. For specific coverage rates that include joint size, and usage efficiencies, visit our website usage calculator at www.tremcosealants.com

Packaging

10.1-fl. oz (300-mL) cartridge, 20-fl. oz (600-mL) sausage, 5-gal (19-L) pail

Colors

Rust Red

Shelf Life

1 year when stored at 40 to 110 °F (5 to 43 °C)

Storage

Store TREMstop IA+ in original, undamaged packaging in a clean, dry, protected location with temperatures between 40 to 110 °F (5 to 43 °C).

Applicable Standards

- UL 1479 (ASTM E 814)
- UL 723 (ASTM E 84)
- UL 2079 (ASTM E 1966)
- CAN/ULC-S115M
- FBC® System Compatible

Fire Rated

Available at: <http://www.tremcosealants.com/technical-resources/fire-systems.aspx>

Limitations

- Not recommended for use with passive fire containment systems not listed or approved by Tremco
- Keep from Freezing

Joint Description

Mineral wool, closed cell, or reticulated polyethylene backer rod is recommended as joint backing to control sealant depth and insure intimate contact of sealant with cavity wall when tooling. Certain types of backing material may be required by system. For additional information on firestop system components, please visit www.tremcosealants.com/commercial/firestop.

Sealant Dimensions

Consult Tremco Passive fire system listed or approved by Tremco

Cure Time

At 77 °F (25 °C), 50% RH, TREMstop IA+ is tack free in 30 to 60 minutes and dries at a rate of about 1/8" (3 mm) per day. As the temperatures decrease, the dry time of TREMstop IA+ will increase, generally one additional day for every 10 °F decrease in temperature.

Clean Up

Excess sealant and smears can be cleaned up or removed with soapy water before sealant skins. Any utensils used for tooling can also be cleaned with soapy water.

Warranty


Tremco warrants its Products to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace, or refund the purchase price of the quantity of Tremco Products proven to be defective and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.



NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TYPICAL VALUES
Type		Single component Intumescent Acrylic Latex sealant
Color		Rust Red
Solids		76%
Specific Gravity		1.38
Application		gun-grade sealant, applied with typical caulking equipment
Flame Spread	ASTM E84	0
Smoke Development	ASTM E84	5
Skin Time	ASTM C679	30 to 60 min at 77 °F (25 °C), 50% RH
CPVC Compatible	Lubrizol FGG/BM/CZ Compatibility Program	Yes
Volume Expansion		8 to 10X
Onset of Expansion, °C	Thermogravimetric Analysis	200
Expansion Temperature Range, °C	Thermogravimetric Analysis	200 to 800



Cleveland 1-800-362-9267
Canton 1-877-258-7601
Toledo 1-800-860-3352
www.chasehipps.com



0220/TSIADS-ST

Tremco Commercial Sealants & Waterproofing

3735 Green Rd
Beachwood OH 44122
216.292.5000 / 800.321.7906

1451 Jacobson Ave
Ashland OH 44805
419.289.2050 / 800.321.6357

220 Wicksteed Ave
Toronto ON M4H1G7
416.421.3300 / 800.363.3213

1445 Rue de Coulomb
Boucherville QC J4B 7L8
514.521.9555